

### Product description

	Unit	
<ul style="list-style-type: none"> <li>Parquet</li> <li>V-Groove</li> <li>Format (L x w x h)</li> <li>Facing thickness genuine hardwood</li> <li>Total thickness</li> <li>Weight</li> <li>Moisture content (when delivered)</li> <li>Core layer</li> <li>Backing layer</li> <li>Species offered</li> <li>Surface treatment</li> <li>Packaging</li> </ul>		Single plank on the long sides 1182 x 165 x 11  2,5 11 9  7-10 Brown HDF thickness 7,2 Softwood veneer 1,5 Oak High Performance Masterresist Lacquer Protective edge with recycled carton (95% recycled paper) Climate protection of PE film 8 planks = 1,56m <sup>2</sup> 66 packs = 102,97m <sup>2</sup> PEFC for Oak 15 years domestic use Lifetime for locking system Mechanical loc: Bestloc and BestLoc X-TREME no glue, no tools (see the installation instructions available on berryalloc.com)
<ul style="list-style-type: none"> <li>Packaging contents</li> </ul>	pack pallet	
<ul style="list-style-type: none"> <li>Environnemental prog.</li> <li>Warranty</li> </ul>		
<ul style="list-style-type: none"> <li>Installation</li> </ul>		
<ul style="list-style-type: none"> <li>Underfloor heating</li> </ul>	DTU 51.11 DTU 51.2	Floating laying (french installation rule) Glued fitting (french installation rule) suitable (see the specific requirements for wood floors above underfloor heating on the web site)

Classification	Norme	Unit	Mesures
<ul style="list-style-type: none"> <li>Abrasion resistance</li> </ul>	CS10 (NF Parquet) EN 13329 (Test S42)	Tour (TT) Tour (TT)	6000-9000 >700
<ul style="list-style-type: none"> <li>Gloss value</li> </ul>		Gloss 60° Gloss 60° Gloss 60°	27 +/- 2 (satin) 15 +/- 2 (patina) 7 +/- 2 (matt)
<ul style="list-style-type: none"> <li>Fire class</li> </ul>	EN 13 501-1	Oak	Dfl-S1
<ul style="list-style-type: none"> <li>Slippery</li> </ul>	XP CEN TS 15676		
<ul style="list-style-type: none"> <li>Adhésion</li> <li>Thermal resistance</li> <li>European class (based on unfinished wood)</li> </ul>	ISO 2409 EN 685	Adhesion coefficient m <sup>2</sup> K/W	1 Oak: 0,066
<ul style="list-style-type: none"> <li>Loc System Joint strength</li> </ul>		Oak Kg / m Kg / m	23 Long side > 550 Short side > 1 000
<ul style="list-style-type: none"> <li>Marquage CE</li> <li>Formaldehyde emission</li> <li>VOC emission</li> </ul>	EN 14342 EN 717-1 ISO 16 000-9	ug/m <sup>3</sup> ug/m <sup>3</sup>	E1 A+

### Maintenance

See instructions on [berryalloc.com](http://berryalloc.com)

For commercial use, please take contact with us.

