

**Product description**

	Unit	
• Parquet		Single plank
• V-Groove (GO2)		On the long sides
• Format (L x w x h)	mm	1180 x 164 x 14
• Facing thickness genuine hardwood	mm	3,3 <sup>+0/-0.1</sup>
• Core layer	mm	HDF thickness 9
• Backing layer	mm	Softwood veneer 1,5
• Total thickness	mm	14
• Weight	kg/m <sup>2</sup>	11
• Moisture content (when delivered)	%	7-10
• Species offered		Frêne, noyer, sapelli
• Surface treatment		High Performance Ultimtec Lacquer
• Packaging		Protective edge with recycled carton (95% recycled paper) Climate protection of PE film
• Packaging contents	pack Pallet	8 planks = 1,5481 m <sup>2</sup> 66 packs = 102,17 m <sup>2</sup>
• Environnemental prog.		PEFC (Walnut and Sapele)
• Warranty		30 years domestic use (see conditions on berryalloc.com) Lifetime for locking system
• Installation		Mechanical loc : Bestloc et BestLoc X-TREME no glue, no tools (see the installation instructions available on berryalloc.com)
	DTU 51.11 DTU 51.2	Floating laying (french installation rule) Glued fitting (french installation rule)
• Underfloor heating		Suitable (see the specific requirements for wood floors above underfloor heating on berryalloc.com)

Classification	Norm	Unit	Measurements
• Abrasion resistance	CS10 (NF Parquet) EN 13329 (Test S42)	Tour (TT) Tour (TT)	15600 (lacquered) >500 (lacquered)
• Gloss value		Gloss 60° Gloss 60° Gloss 60°	27 <sup>+/-2</sup> (satin lacquered) 15 <sup>+/-2</sup> (patina lacquered) 7 <sup>+/-2</sup> (matt lacquered) Dfl-S1
• Fire class	EN 13 501-1	Noyer, Sapelli, Frêne	70,5 % (18,8 %) (lacquered)
• Slippery	XP CEN TS 15676	SRT Longitudinal (CV %) SRT Transversal (CV %)	79,2 % (12,8 %) (lacquered) 0
• Adhesion	ISO 2409	Adhesion	
• Thermal resistance		coefficient m <sup>2</sup> K/W	Walnut : 0,081 Sapele : 0,079 Ash : 0,078
• European class (based on unfinished wood)	EN 685	Ash / Sapele Walnut	31 22
• Loc System Joint strength		Kg / m Kg / m	Long side > 550 Short side > 1000
• CE Mark	EN 14342		
• Formaldehyde emission	EN 717-1	µg/m <sup>3</sup>	E1
• VOC emission	ISO 16 000-9	µg/m <sup>3</sup>	A+

**Maintenance**

See instructions on berryalloc.com

**For commercial use, please take contact with us.**
