

Product description

Product description	Unit	
• Parquet		Single plank
• V-Groove (GO2)		On the long sides
• Format (L x w x h)	mm	1980 x 130 x 14
• Facing thickness genuine hardwood	mm	3,3 ^{+0/-0.1}
• Core layer	mm	HDF thickness 9
• Backing layer	mm	Softwood veneer 1,5
• Total thickness	mm	14
• Weight	kg/m ²	11
• Moisture content (when delivered)	%	7-10
• Species offered		Oak
• Surface treatment		Lacquered Ultimtec, oiled
• Packaging		Protective edge with recycled carton (95% recycled paper) Climate protection of PE film
• Packaging contents	pack Pallet	6 planks = 2,06 m ² 48 packs = 98,84 m ²
• Environnemental prog.		PEFC (Oak)
• Warranty		30 years domestic use (voir conditions sur www.berryalloc.com) Lifetime for locking system
• Installation		Mechanical loc: Bestloc and BestLoc X-TREME no glue, no tools (see the installation instructions available on berryalloc.com) DTU 51.11 Floating laying (french installation rule) DTU 51.2 Glued fitting (french installation rule)
• Underfloor heating		Suitable (see the specific requirements for wood floors above underfloor heating on berryalloc.com)

Classification	Norm	Unit	Measurements
• Abrasion resistance	CS10 (NF Parquet) EN 13329 (Test S42)	Tour (TT) Tour (TT)	15600 (lacquered) >500 (lacquered)
• Gloss value		Gloss 60°	7 ^{+/-2} (matt lacquered)
• Fire class	EN 13 501-1	Oak	Dfl-S1
• Slippery	XP CEN TS 15676	SRT Longitudinal (CV %) SRT Transversal (CV %)	70,5 % (18,8 %) (lacquered) 79,2 % (12,8 %) (lacquered)
• Adhesion	ISO 2409	Adhesion	0
• Thermal resistance		coefficient m ² K/W	Oak: 0,080
• European class (based on unfinished wood)	EN 685	Oak	31
• Loc System Joint strength		Kg/m Kg/m	Long side > 550 Short side > 1000
• CE Mark	EN 14342		
• Formaldehyde emission	EN 717-1	µg/m ³	E1
• VOC emission	ISO 16 000-9	µg/m ³	A+

Maintenance

See instructions on berryalloc.com

For commercial use, please take contact with us.

