ocean.
technical data

BERRY ALLOC

08/2022

	contains	m²	ft²	weight
1 pack Ocean	9 planks	2,20 m²	23.71 ft²	15,7 kg
1 pallet Ocean	56 packs	123,34 m²	1327.61 ft²	891 kg

hydro+

product specifications

Dimensions	1288 x 190 mm
Total thickness	8 mm
Bevels	0
Loc System	DuoLoc
Level of use according to European standard EN10874	23 heavy domestic use
	32 general commercial use
Residential warranty	lifetime
Commercial warranty	5 years

Warranty conditions on www.berryalloc.com

composition

Surface layer	Direct laminated paper, impregnated with melamine resin
Substrate	Moisture resistant High Density Fiberboard (HDF) treated with hydro+ water repelling technology
Backing	Direct laminated paper, impregnated with melamine resin

test results

Abrasion resistance	EN13329	AC4 (IP≥4000)
Impact resistance	EN13329	Small ball : ≥ 12 N - Big ball : ≥ 750 mm
Thickness swelling	EN13329	12% (requirement ≤ 18%)
Fire resistance	EN14041	Cfl-S1
Formaldehyde emission	EN14041	E1
Slip resistance	EN14041	DS
Density	EN323	900 kg/m³
Resistance to staining	EN438	5 (groups 1+2) ; 4 (group 3)
Effect of a furniture leg	EN424	No damage (foot type 0)
Effect of a castor chair	EN425	No change in appearance or damage
Thermal resistance in combination with underlay Excellence Plus	ISO 8302	0,08 m²K/W – Suitable for floor heating/cooling. Detailed instructions on www.berryalloc.com

certificates/labels

- DOP : 170-DPLA18-1
  UKCA : 170-DPLA22-1
- Sustainability of forests :
  PEFC certified (07-31-229)
- Labelling according to French VOC emission regulation: A+

EN 14041
CE 18 DOP 170-DPLA18-1 | UKCA 22 DOC UK 170-DPLA22-1
Berryalloc NV
Industrielaan 100
8930 Menen, Belgium
NB 1161
Laminate floor covering for use within building
www.berryalloc.com

PEFC Certified
Laminate comes from Sustainably Managed Forests, recycled or controlled sources.
PEFC
PEFC/07-31-229
www.pefc.org

ÉMISSIONS DANS L'AIR INTÉRIEUR*
A+
A+ A B C
*Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

23
32

laminate.