










Test	Commodore 800	Commodore 1000	Commodore 1200	Emperor 1000	Emperor 1200	Emperor 1450
Manufacturing technique Herstellungstechnik Technique de fabrication	1/10 printed saxony 1/10 Druck-Saxony 1/10 saxony imprimée	1/10 printed saxony 1/10 Druck-Saxony 1/10 saxony imprimée	1/10 printed saxony 1/10 Druck-Saxony 1/10 saxony imprimée	1/10 printed saxony 1/10 Druck-Saxony 1/10 saxony imprimée	1/10 printed saxony 1/10 Druck-Saxony 1/10 saxony imprimée	1/10 printed saxony 1/10 Druck-Saxony 1/10 saxony imprimée
Pile composition Material der Nutzschrift Composition du velours	100% PA 6.0 Crealton  	100% PA 6.0 Crealton  	100% PA 6.0 Crealton  	100% PA 6 	100% PA 6 	100% PA 6 
Secondary backing Rückenausstattung Dossier	Weaveback	Weaveback	Weaveback	Weaveback	Weaveback	Weaveback
Width Breite Largeur	400 cm	400 cm	400 cm	400 cm	400 cm	400 cm
Roll length Rollenlänge Longeur du rouleau	25 m	25 m	25 m	25 m	25 m	25 m
Pile height Polhöhe Hauteur du velours	ISO 1766 6 mm	7 mm	8 mm	6 mm	6 mm	7 mm
Pile weight Polgewicht Poids du velours	800 g/m ²	1000 g/m ²	1200 g/m ²	1000 g/m ²	1200 g/m ²	1450 g/m ²
Total height Gesamthöhe Hauteur totale	ISO 1765 8 mm	9 mm	10,5 mm	8 mm	8,5 mm	10 mm
Total weight Gesamtgewicht Poids total	ISO 8543 1945 g/m ²	2065 g/m ²	2265 g/m ²	2055 g/m ²	2200 g/m ²	2370 g/m ²
Number of tufts Noppenzahl Nombre de points	ISO 1763 161 400/m ²	200 700/m ²	216 500/m ²	173 200/m ²	185 000/m ²	204 700/m ²
Minimum order quantity Mindestabnahme Quantité minimum	300 m ² /colourbank 300 m ² /Farbbank 300 m ² /banque de couleurs	300 m ² /colourbank 300 m ² /Farbbank 300 m ² /banque de couleurs	300 m ² /colourbank 300 m ² /Farbbank 300 m ² /banque de couleurs	300 m ² /colourbank 300 m ² /Farbbank 300 m ² /banque de couleurs	300 m ² /colourbank 300 m ² /Farbbank 300 m ² /banque de couleurs	300 m ² /colourbank 300 m ² /Farbbank 300 m ² /banque de couleurs
Fastness to rubbing (dry) Reibechtheit (trocken) Solidité au frottement (sec)	ISO 105 X12 4-5	4-5	4-5	4-5	4-5	4-5
Fastness to rubbing (wet) Reibechtheit (mass) Solidité au frottement (humide)	ISO 105 X12 4-5	4-5	4-5	4-5	4-5	4-5
Water fastness Wasserechtheit Solidité à l'eau	ISO 105 E01 4-5	4-5	4-5	4-5	4-5	4-5
Fastness to light Lichtechtheit Solidité à la lumière	ISO 105 B2 5	5	5	5	5	5
Thermal resistance Wärmedurchlasswiderstand Résistance thermique	ISO 8302 0,072 m ² K/W	0,0813 m ² K/W	0,0921 m ² K/W	0,072 m ² K/W	0,077 m ² K/W	0,083 m ² K/W
Impact sound insulation Trittschalldämmung Réduction de la transmission du bruit de choc	ISO 140 - 8 25 dB	28 dB	32 dB	28 dB	30 dB	32 dB
DOP Nr / DOP n°	1087#00573/WICR	1087#00554/WICR	1087#00462/WICR	1087#00576/WICR	1087#00577/WICR	1087#00578/WICR
