

## Product description

	Unit			
<ul style="list-style-type: none"> <li>Parquet</li> <li>V-Groove</li> <li>Format (L x w x h)</li> <li>Facing thickness genuine hardwood</li> <li>Total thickness</li> <li>Weight</li> <li>Moisture content (when delivered)</li> <li>Core layer</li> <li>Backing layer</li> <li>Species offered</li> <li>Surface treatment</li> <li>Packaging</li> </ul>	mm	Single plank on the long sides <b>Saga XL</b> 1980 x 187 x 14	<b>Saga</b>	<b>1180 x 187 x 14</b>
	mm	3,3		
	mm	14		
	kg/m <sup>2</sup>	11		
	%	7-10		
	mm	Brown HDF thickness 9,2		
	mm	Softwood veneer 1,5		
		Oak		
		<b>Oiled</b>		
		Protective edge with recycled carton (95% recycled paper)		
		Climate protection of PE film		
<ul style="list-style-type: none"> <li>Packaging contents</li> </ul>	pack pallet	<b>Saga XL</b> 6 planks = 2,2m <sup>2</sup> <b>Saga XL</b> 40 packs = 88,86m <sup>2</sup>	<b>Saga</b> <b>Saga</b>	<b>8 planks = 1,76m<sup>2</sup></b> <b>40 packs = 70,61m<sup>2</sup></b>
<ul style="list-style-type: none"> <li>Environnemental prog.</li> <li>Warranty</li> </ul>		PEFC for Oak 30 years domestic use Lifetime for locking system		
<ul style="list-style-type: none"> <li>Installation</li> </ul>		Mechanical loc: Bestloc and BestLoc X-TREME no glue, no tools (see the installation instructions available on berryalloc.com)		
		Floating laying (french installation rule)		
		Glued fitting (french installation rule)		
<ul style="list-style-type: none"> <li>Underfloor heating</li> </ul>	DTU 51.11 DTU 51.2	suitable (see the specific requirements for wood floors above underfloor heating on berryalloc.com)		

Classification	Norme	Unit	Mesures
<ul style="list-style-type: none"> <li>Abrasion resistance</li> </ul>	CS10 (NF Parquet) EN 13329 (Test S42)	Tour (TT) Tour (TT)	/ oiled >
<ul style="list-style-type: none"> <li>Gloss value</li> </ul>		Gloss 60° Gloss 60° Gloss 60°	/ oiled
<ul style="list-style-type: none"> <li>Fire class</li> </ul>	EN 13 501-1	Oak	Dfl-S1 (after finishing)
<ul style="list-style-type: none"> <li>Slippery</li> </ul>	XP CEN TS 15676		
<ul style="list-style-type: none"> <li>Adhésion</li> <li>Thermal resistance</li> <li>European class (based on unfinished wood)</li> </ul>	ISO 2409 EN 685	Adhesion coefficient m <sup>2</sup> K/W	Oak: 0,080
<ul style="list-style-type: none"> <li>Loc System Joint strength</li> </ul>		Oak Kg / m Kg / m	31 Long side > 550 Short side > 1 000
<ul style="list-style-type: none"> <li>Marquage CE</li> <li>Formaldehyde emission</li> <li>VOC emission</li> </ul>	EN 14342 EN 717-1 ISO 16 000-9	ug/m <sup>3</sup> ug/m <sup>3</sup>	E1 A+

## Maintenance

See instructions on berryalloc.com

**For commercial use, please take contact with us.**

